


AIRDUC® PUR 350 FOOD-AS (MD)



Antistatic food hose and pharmaceutical hose, medium-heavy duty

Applications

- flexible hose/ ducting for abrasive powder, bulk material, granulate and for gases
- food industry, pharmaceutical industry: food, pharmaceutical
- conveying of dry foods e.g. rice, cereals, sugar, milk powder, powders, coffee, tea, grains, flour, frozen foods
- mixer, dryer, packaging machine, bulk-bag (big bag)-charging and discharging, mill
- explosion hazard area
- clean room ventilation, semiconductor production machine
- paper mill, paper and pulp industry: waste water, air extraction
- medical equipment/ medical technology, healthcare sector: cable protection conduit, air supply hose, extraction hose
- municipal vehicle: lawn mower, slope mower, leaf blower/ leaf collector

Properties

- medium-heavy duty

- highly abrasion resistant
- Food grade wall, complies with: EU-Directive 10/2011, EC 1935/2004 and EU 2015/174, FDA 21 CFR 177.2600
- odorless and tasteless
- microbe and hydrolysis resistant
- good resistance to oil, gasoline, and chemicals
- very good low temperature flexibility
- Permanently antistatic wall: according to ISO 8031 electrical and surface resistance $<10^9 \Omega$ (according to TRGS 727 $<2,5 \cdot 10^8 \Omega \cdot m$ and NFPA 652 $10^8-10^9 \Omega$)
- in accordance with ATEX 2014/34/EU (1999/92/EC) and German TRGS 727: pneumatic transport of flammable dusts and bulk materials (Zone 20, 21, 22 inside), aspiration of combustible dusts (Zone 22 inside),
- in accordance with ATEX 2014/34/EU (1999/92/EC) and German TRGS 727: for conveying for flammable liquids (inside zone 0, 1, 2), for conveying for non-flammable liquids, for use in zone 1 and 2 (gases), for use in zone 0 (gases)
- according to DIN 26057 Type 2
- manufacturing process acc. GMP EC 2023/2006
- conforms to RoHS guideline

- REACH according to --> Technology / Technical Information / REACH

Temperature range

- 40 °F to 195 °F
- short time to 255 °F

Design

- AIRDUC® profile hose
- spring steel wire firmly embedded in wall
- wall: permanently antistatic premium ether-polyurethane (Pre-PUR®)
- wall thickness 0.0275 in approx.

Delivery variants

- further diameters and lengths available on request
- transparent (standard)
- customer-specific branding

I.D. (in / mm)	outer Ø (in)	Pressure DIN 26057 (50% Elongation) (psi)	Vacuum DIN 26057 (axially fixed) (inHG)	Bending radius (in)	Weight (lb/ft)	Dimensions in Stock (ft)	Production lengths (ft)	Order No.
standard								
1 / 25	1.260	35.462 (79.047)	22.295 (29.530)	0.906	0.134	25 50	-	350-0025-0000
- / 30	1.457	29.806 (66.283)	18.604 (29.530)	1.024	0.161	-	25 50	350-0030-0000
1,25 / 32	1.535	27.993 (62.222)	17.423 (29.530)	1.063	0.168	-	25 50	350-0032-0000
1,36 / 35	1.654	25.672 (57.146)	15.946 (29.530)	1.142	0.181	-	25 50	350-0035-0000
1,5 / 38	1.772	23.714 (52.795)	14.617 (29.530)	1.220	0.195	25 50	-	350-0038-0000
- / 40	1.850	22.554 (50.184)	13.879 (29.530)	1.260	0.208	-	25 50	350-0040-0000
1,75 / 44-45	2.047	20.161 (44.672)	12.403 (29.530)	1.378	0.228	-	25 50	350-0045-0000
2 / 50-51	2.244	18.130 (40.321)	11.221 (29.530)	1.496	0.255	25 50	-	350-0050-0000
- / 55	2.441	16.535 (36.695)	10.188 (29.235)	1.614	0.276	-	25 50	350-0055-0000
2,36 / 60	2.638	15.229 (33.794)	9.302 (24.510)	1.732	0.302	-	25 50	350-0060-0000
2,5 / 63-65	2.756	14.069 (31.184)	8.564 (20.966)	1.850	0.323	25 50	-	350-0065-0000
- / 70	3.031	13.054 (29.008)	5.463 (24.510)	1.969	0.343	-	25 50	350-0070-0000

Positive and negative pressure ratings are the recommended maximum operating values. Products can be manufactured to meet higher operating values upon request. The bend radius is calculated from the center of the hose in an arched position. Additional information at www.norres.com/us/technology/. NORRES reserves the right to modify technical data at any time. Technical data based on tests at 68 °F and are approx. values. Proper use and maintenance of NORRES hoses is the sole responsibility of purchaser and ultimate user of the product. The individual conditions, applications and the number of variables make firm recommendations technically impossible. This information is intended as a general guide only.


AIRDUC® PUR 350 FOOD-AS (MD)

I.D.	outer Ø	Pressure DIN 26057 (50% Elongation)	Vacuum DIN 26057 (axially fixed)	Bending radius	Weight	Dimensions in Stock	Production lengths	Order No.
(in / mm)	(in)	(psi)	(inHG)	(in)	(lb/ft)	(ft)	(ft)	
3 / 75-76	3.228	12.183 (27.122)	5.168 (21.262)	2.087	0.370	25 50	-	350-0075-0000
- / 80	3.425	11.458 (25.382)	4.725 (18.899)	2.205	0.390	-	25 50	350-0080-0000
3,5 / 89-90	3.819	10.225 (22.626)	4.282 (15.060)	2.441	0.437	25 50	-	350-0090-0000
4 / 100-102	4.213	9.210 (20.451)	3.987 (19.490)	2.677	0.578	25 50	-	350-0100-0000
- / 110	4.606	8.340 (18.565)	3.691 (16.242)	2.913	0.625	-	25 50	350-0110-0000
4,5 / 114-115	4.803	7.977 (17.695)	3.544 (14.765)	3.031	0.652	25 50	-	350-0115-0000
4,72 / 120	5.000	7.687 (16.970)	3.396 (13.584)	3.150	0.679	-	25 50	350-0120-0000
5 / 125-127	5.197	7.397 (16.390)	3.248 (12.403)	3.268	0.712	25 50	-	350-0125-0000
- / 130	5.394	7.107 (15.664)	3.101 (11.517)	3.386	0.733	-	25 50	350-0130-0000
5,5 / 140	5.787	6.599 (14.649)	2.805 (9.745)	3.622	0.786	25 50	-	350-0140-0000
6 / 150-152	6.181	6.164 (13.634)	2.215 (10.631)	3.858	0.867	25 50	-	350-0150-0000
6,3 / 160	6.575	5.802 (12.764)	2.067 (9.154)	4.094	0.914	-	25 50	350-0160-0000
- / 170	6.969	5.439 (12.038)	1.919 (8.268)	4.252	1.062	25 50	-	350-0170-0000
- / 175	7.165	5.294 (11.748)	1.919 (7.678)	4.449	1.001	-	25 50	350-0175-0000
7 / 178-180	7.362	5.149 (11.313)	1.772 (7.087)	4.567	1.028	25 50	-	350-0180-0000
8 / 200-203	8.150	4.641 (10.298)	1.624 (5.611)	5.039	1.149	25 50	-	350-0200-0000
- / 225	9.134	4.134 (9.138)	1.477 (4.430)	5.630	1.277	-	25	350-0225-0000
- / 250	10.118	3.699 (8.267)	1.329 (3.544)	6.220	1.418	10	5 15	350-0250-0000
10 / 254	10.276	3.626 (8.122)	1.329 (3.248)	6.299	1.438	25 50	-	350-0254-0000
- / 275	11.102	3.336 (7.397)	1.181 (2.658)	6.811	1.559	-	25	350-0275-0000
11 / 280	11.299	3.336 (7.397)	1.181 (2.658)	6.929	1.586	25	-	350-0280-0000
- / 300	12.087	3.118 (6.817)	1.034 (2.362)	7.402	1.694	-	25	350-0300-0000
- / 350	14.055	2.683 (5.802)	0.886 (1.477)	8.583	1.976	-	25	350-0350-0000
14 / 356	14.291	2.611 (5.802)	0.886 (1.772)	8.740	2.016	25	-	350-0356-0000
- / 400	16.024	2.321 (5.076)	0.886 (1.477)	9.764	2.554	-	25	350-0400-0000
- / 450	17.992	2.031 (4.641)	0.738 (1.181)	11.063	2.876	-	25	350-0450-0000

neutral imprint: <ID> antistatic + microbe resistant <neutral batch no.> / no cutting

1,5 / 38	1.772	23.714 (52.795)	14.617 (29.530)	1.220	0.208	-	25 50	350-0038-0007
- / 40	1.850	22.554 (50.184)	13.879 (29.530)	1.260	0.222	-	25 50	350-0040-0007
2 / 50-51	2.244	18.130 (40.321)	11.221 (29.530)	1.496	0.269	-	25 50	350-0050-0007
2,5 / 63-65	2.756	14.069 (31.184)	8.564 (20.966)	1.850	0.349	-	25 50	350-0065-0007
- / 70	3.031	13.054 (29.008)	5.463 (24.510)	1.969	0.376	-	25 50	350-0070-0007
- / 75	3.228	12.183 (27.122)	5.168 (21.262)	2.087	0.397	-	25 50	350-0075-0007
- / 80	3.425	11.458 (25.382)	4.725 (18.899)	2.205	0.430	-	25 50	350-0080-0007
4 / 100-102	4.213	9.210 (20.451)	3.987 (19.490)	2.677	0.538	-	25 50	350-0100-0007
4,72 / 120	5.000	7.687 (16.970)	3.396 (13.584)	3.150	0.638	-	25 50	350-0120-0007
5 / 125-127	5.197	7.397 (16.390)	3.248 (12.403)	3.268	0.659	-	25 50	350-0125-0007
5,5 / 140	5.787	6.599 (14.649)	2.805 (9.745)	3.622	0.733	-	25 50	350-0140-0007
6 / 150-152	6.181	6.164 (13.634)	2.215 (10.631)	3.858	0.941	-	25 50	350-0150-0007
6,3 / 160	6.575	5.802 (12.764)	2.067 (9.154)	4.094	1.008	-	25 50	350-0160-0007
7 / 178-180	7.362	5.149 (11.313)	1.772 (7.087)	4.567	1.122	-	25 50	350-0180-0007
8 / 200-203	8.150	4.641 (10.298)	1.624 (5.611)	5.039	1.250	-	25 50	350-0200-0007

Accessories



Positive and negative pressure ratings are the recommended maximum operating values. Products can be manufactured to meet higher operating values upon request. The bend radius is calculated from the center of the hose in an arched position. Additional information at www.norres.com/us/technology/. NORRES reserves the right to modify technical data at any time. Technical data based on tests at 68 °F and are approx. values. Proper use and maintenance of NORRES hoses is the sole responsibility of purchaser and ultimate user of the product. The individual conditions, applications and the number of variables make firm recommendations technically impossible. This information is intended as a general guide only.

AIRDUC® PUR 350 FOOD-AS (MD)

CLAMP 217



CONNECT MOULD ASSEMBLY 233



CLAMP 210 BRIDGE CLAMP

CONNECT DAIRY FITTING 247



CONNECT THREAD FITTING 234



CONNECT 245 FOOD

CONNECT ASEPTIC FITTING 249




CONNECT 246 FOOD



CONNECT 240 + 241 FOOD

CONNECT 223



CONNECT 244 FOOD



CONNECT 228



CONNECT 270-271



CONNECT 243 FOOD



CLAMP 212



CLAMP 213



CONNECT TRI-CLAMP FITTING 245